



WECRF COLD BOND CEMENT & HARDENER



Photo shows 800 ml / .25 gal cement with 35 gr / 1.2 oz hardener.

WECRF is the ideal cement for conveyor belt repair and splicing. It is also excellent for use on wood, fiberglass, concrete, urethane, steel, rubber and fabric.

FEATURES

- WECRF is an ethyl acetate based chloroprene cement and is available in four different sizes
- Free of chlorinated hydrocarbons
- High initial and permanent adhesion
- Easy to process
- Offers higher threshold limit values than for chlorinated hydrocarbons

WECRF HARDENER

| PRODUCT CODE | GRAM | OUNCE |
|--------------|------|-------|
| CC-WECRF-018 | 18 | .63 |
| CC-WECRF-035 | 35 | 1.2 |

WECRF COLD BOND CEMENT

| PRODUCT CODE | VOLUME | | WEIGHT | | COVERAGE | | HARDENER BOTTLE QUANTITY |
|--------------|--------|-----|--------|-----|----------------|-----------------|--------------------------|
| | LITER | GAL | KG | LBS | M ² | FT ² | |
| CC-WECRF-001 | .4 | .12 | .25 | .5 | 1.4 | 15 | 1 CH-WECRF-018 |
| CC-WECRF-002 | .8 | .25 | .7 | 1.5 | 2.8 | 30 | 1 CH-WECRF-035 |
| CC-WECRF-010 | 4 | 1 | 3.5 | 7.5 | 14 | 150 | 5 CH-WECRF-035 |
| CC-WECRF-200 | 200 | 50 | 175 | 386 | 695 | 7500 | 250 CH-WECRF-035 |

| WECRF CEMENT | |
|---------------------|------------------------------------|
| Colour | White |
| Pot Life | 4 Hours @ 21 °C / 70 °F |
| Working Temperature | -23 °C to 82 °C / -10 °F to 180 °F |
| Shelf Life | 24 months in a cool, dark location |



Note: The above data is based on extensive testing and represents standard values. Shaw Almex Industries reserves the right to make changes without prior notice and refuses all claims arising from such changes. All items are subject to change without previous notice.