

ECRF COLD FUSION CEMENT & HARDENER



Photo shows 800 ml / .25 gal cement with 35 gr / 1.2 oz hardener.

ECRF is the ideal cement for conveyor belt repair and splicing, and is excellent for use on wood, fiberglass, concrete, urethane, steel, rubber and fabric.

FEATURES

- ECRF is an ethyl acetate based chloroprene cement, and is available in four sizes
- Free of chlorinated hydrocarbons
- High initial and permanent adhesion
- Easy to process
- Offers higher threshold limit values than for chlorinated hydrocarbons
- Flammable

ECRF HARDENER

	PRODUCT CODE	GRAM	OUNCE
	CH-ECRF-018	18	.63
ı	CH-ECRF-035	35	1.2

ECRF COLD BOND CEMENT

	VOLUME		WEIGHT		COVERAGE	
PRODUCT CODE	LITER	GAL	KG	LBS	M²	FT ²
CC-ECRF-001	.4	.12	.35	.8	1.4	15
CC-ECRF-002	.8	.20	.7	1.5	2.8	30
CC-ECRF-010	4	1	3.5	7.7	14	150
CC-ECRF-200	200	50	175	386	695	7500

HARDENER BOTTLE QUANTITY			
1 CH-ECRF-018			
1 CH-ECRF-035			
5 CH-ECRF-035			
250 CH-ECRF-035			

ECRF PROPERTIES	
Colour	Black
Pot Life	4 Hours @ 21 °C / 70 °F
Working Temperature	-23 °C to 82 °C / -10 °F to 180 °F
Shelf Life	24 months in a cool, dark location



Note: The above data is based on extensive testing and represents standard values. Shaw Almex Industries reserves the right to make changes without prior notice and refuses all claims arising from such changes. All items are subject to change without previous notice.