

# HFP

## FABRIC BELT PRIMER

**HFP** is a one-part coating for RFL treated fabric that enhances adhesions in vulcanized belt splicing. It is designed for use as a reactive bonding agent between bare fabric surfaces and uncured splice materials.

### FEATURES:

- Prepares the clean work surface for tackifying and increases the bond
- Tested for compatibility with all major conveyor belting manufacturer specifications
- Brushable consistency for ease of application
- Good penetration into RFL treated fabric
- Use for Natural Rubber (NR), Polyisoprene (IR), Styrene-Butadiene (SBR), Polybutadiene (BR), Polychloroprene i.e. Neoprene (CR) rubber belt splices
- Flammable

#### Product Information Properties:

Rubber Colour: Black  
 Base Polymer: Mix of Polymers  
 Solids (wt.): 20-25%  
 Calculated Coverage: 13.4 M<sup>2</sup> (144 ft.<sup>2</sup>)  
 Flash Point: 26 °C (79 °F)  
 Shelf Life: 6 Months at 21 °C (70 °F) or  
 12 Months at 10 °C (50 °)



PRODUCT CODE	WEIGHT (METRIC/IMPERIAL)
AA-HFP-Q	750 gr / 1.7 Lbs.

NA